

Amendment to the Specification

I. Please replace paragraph [0025] of the instant application with:

“[0025] In step (b) of the above-mentioned five embodiments of the present invention, a monomer [[and]] or waste polyamide producing polyamide may be additionally added and reacted to produce a polyamide block. Preferably, the monomer [[and]] or waste polyamide are added in content of 1 to 90% by weight to the prepared polymer.”

II. Please replace paragraph [0041] of the instant application with:

“[0041] Polyamide-producing monomer [[and]] or waste polyamide that can be used in step (b) are at least one of waste materials selected from the group consisting of lactams containing more than 6 carbon atoms such as epsilon-caprolactam and lauryl lactam; aliphatic amino carboxylic acids such as amino caproic acid, 7-aminoheptanoic acid, 11-aminoundecanoic acid, 12-aminododecanoic acid; polycondensation products of diacid and diamine such as hexamethylenediamine diadipate; and waste polyamides such as 6-nylon, 6,6-nylon, 11-nylon, and 12-nylon.”